

## PRODUCT INFORMATION BULLETIN

# DPF 4500G Vinyl Film

## Intermediate Calendered Digital Print Pressure Sensitive Film

### PRODUCT DESCRIPTION

DPF 4500G is a 3-mil gloss white calendered film with permanent pressure-sensitive adhesive. Designed for indoor and outdoor promotional graphics, DPF 4500G is made of 100% polymeric face stock with a clay-coated kraft liner. The special glossy face stock is designed for applications requiring High Gloss or more image "pop." DPF 4500G is rated for outdoor durability up to 5 years (unprinted). Printed durability is dependent on the ink system used.

### AREAS OF USE

- Digital printing with a wide variety of direct print systems, including Encad® VinylJet™
- Promotional and merchandising graphics
- Shorter-term signage, kiosks, POP displays, real estate signage, transit graphics, fleet or vehicle markings and decals

### PERFORMANCE AND PHYSICAL DATA

<u>PROPERTY</u>	<u>TEST METHODS</u>	<u>TYPICAL VALUE</u>	
<b>SURFACE FINISH</b>	Gloss Meter 60° Reflection	80-90%	
<b>THICKNESS</b> (including adhesive)	Micrometer, Federal Bench Type	0.0043 in	0.11 mm
<b>TENSILE STRENGTH</b>	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	13.0 lb/in width	2.3 kg/cm width
<b>ELONGATION</b>	Instron Tensile Tester as above	≥150%	
<b>SHELF LIFE</b>	Free from excessive moisture, temperature, direct sunlight	1 year from factory shipment	
<b>APPLICATION TEMPERATURE RANGE</b>	On clean, dry substrate	60°F to 90°F optimum	16°C to 32°C optimum
<b>SERVICE TEMPERATURE RANGE</b>	On clean, dry substrate	-20°F to 150°F	-29°C to 65° C
<b>DIMENSIONAL STABILITY</b>	158°F (70°C), 48 hours	25 mils	0.64 mm
<b>PEEL ADHESION</b>	PSTC-1, 15 min, RT 70°F (21°C)	2.5 lbs/in	0.45 kg/cm
<b>LINER RELEASE</b>	TLMI Release at 90°, 300 in/min (760 cm/min)	100 g/2 in	39 g/cm

Standard Terms and Conditions Apply

Effective 1998  
Revision:08/2006

## CONDITIONS OF SALE

*The following is made in lieu of all warranties expressed or implied:*

All statements, technical information and recommendations published by Arlon, Inc. relating to DPF products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon, Inc. makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon, Inc. shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.



[www.arlon.com](http://www.arlon.com)

### USA

2811 S. Harbor Blvd  
Santa Ana, CA 92704  
Phone: (714) 540-2811 / (800) 854-0361  
Fax: (714) 540-7190 / (800) 329-2756

### EUROPE

Badhuisweg 11  
2587 CA Den Haag  
The Netherlands  
Phone: +31 (0) 70 354-4311  
Fax: +31 (0) 70 355-7721

©Arlon 1998  
2616P 10/02  
Revision: 08/2006